

Fujicolor Crystal Archive Supreme Paper

Equipment		Software	Calibration data			
Brand	Name		LUT + Target density RGB Glossy / Lustre	Basic calibration ymcd	Intermittance rgb	Thickness
Frontier	3xx	Installer R	LUT C + surface selection	n.a	n.a	n.a
	5xx	Installer R	LUT C + surface selection			
	7xx	N3.12	LUT C-1			
Noritsu	QSS 28x ~ LP24Pro	Vol.713	163	n.a.	n.a.	n.a.
	35xx, 37xx	N3.12	163			
Agfa	DLab 1, 2, 3		2.00 / 2.00 / 1.95	0.97 / 1.00 / 1.02		
KIS	DKS 15x, 16x, 17x		Printer defines own and highest possible Dmax settings (exposure vs chemistry relation)			
ISAG	Fastprint		2.00 / 2.00 / 1.95	n.a.	n.a.	0.22
	Wideprint 8", 12"					
	Wideprint R2R		163	n.a.	n.a.	n.a.
ZBE Chromira	SE, Pro, R2R		2.00 / 2.00 / 1.95	n.a.	n.a.	n.a.
Polielettronica	Laserlab 50/76		Printer defines own and highest possible Dmax settings (exposure vs chemistry relation)			
Durst	Epsilon		2.00 / 2.00 / 1.95	0.004 / 0.056 / 0.000 / 0.920	90 / 50 / 37	n.a.
	Zeta					
	Theta 50/51			170.2 / 112.0 / 0.0 / 104.3		
	Theta 76/76HS			0.006 / 0.085 / 0.000 / 1.325	101 / 56 / 42	

All recommended Dmax values can only be reached when using high active chemistry equal to Fujifilm CPRA Digital Pro AC and Fujifilm ADM chemistry
For competitive and recycling chemistry the Dmax should be reduced with -0.10 density

* Profiles location : http://products.fujifilm.eu/support/color_management/photographic/